

WTCB
TESTED

MULTI

PRIMER FOR BRICKS WITH VARYING MOISTURE ABSORPTION



Description

The past few years, we have seen a rise in building materials that are very hard to prime (to remove absorption), even with the best of primers. Generally speaking, it concerns foreign bricks with varying colours. They are often characterised by strongly varying absorption. After years of research and tests on these surfaces, Cosmar has finally come up with an answer that will allow you to work effectively on these surfaces. **MULTI** prevents the phenomenon of 'burning' of the plaster. Thanks to its unique and double action it also prevents the plaster drying up too quickly or irregularly. Because of that, the plaster remains sufficiently moist to be able to be worked on until a qualitative finish can be attained. Although good results can be achieved with plaster, **MULTI** is however not suited to be used to fix mortars or cement. The vapour permeability of the treated surface remains unchanged. **MULTI** is to be used for interior applications only.



Instructions

- * Dilute **MKS** to a ratio of 1 liter of product to 9 liters of water.
- * Apply with a sprayer or with a brush and roll.
- * It is to be applied from bottom to top, in horizontal back and forth movements until a satisfactory flow is achieved.
- * When it has dried (takes about 6 hours), the application of plaster may begin.
- * After usage, clean tools with water



Precautions

- * The surface must be clean, structurally sound, fully dry, and free of oil and grease.
- * Neutralise and eliminate any salt efflorescence with **PRO-BRIK**
- * Do not apply immediately after a rainshower or after long periods of rain, in order to ensure optimum saturation of the product.
- * The ideal temperature to apply is between 5°C and 30°C
- * Protect windows, glazing, metals and plants during the treatment.
- * Remove any remains of silicone glue with our product **CLEAN FORCE**



Fysical properties

- * appearance: liquid, white
- * not water soluble
- * contains potassium methyl silicate
- * not environmentally dangerous



Consumption

A surface of about 60-80 m² can be treated with a litre of diluted product, depending on the pore structure of the surface to be treated.



Storage

Store and transport the product frost free.

